

# Vortex dynamics of a $d + is$ -wave superconductor

Qunqing Li<sup>1</sup>, Z. D. Wang<sup>1</sup>, and Qiang-Hua Wang<sup>1,2</sup>

<sup>1</sup>*Department of Physics, University of Hong Kong, Pokfulam Road, Hong Kong, China*

<sup>2</sup>*National Laboratory of Solid State Microstructures, Institute for Solid State Physics, Nanjing University, Nanjing 210093, China*

The vortex dynamics of a  $d + is$ -wave superconductor is studied numerically by simulating the time-dependent Ginzburg-Landau equations. The critical fields, the free flux flow, and the flux flow in the presence of twin-boundaries are discussed. The relaxation rate of the order parameter turns out to play an important role in the flux flow. We also address briefly the intrinsic Hall effect in  $d$ - and  $d + is$ -wave superconductors.

74.20.De, 74.60.-w

In recent years the symmetry of the pairing function has been one of the interesting topics in the field of high temperature superconductor. It is widely accepted that the dominant pairing wave function has a  $d_{x^2-y^2}$  symmetry, as supported by experiments using phase-sensitive devices, such as Josephson junctions or Superconducting Quantum Interference Devices (SQUID).<sup>1-5</sup> However, the subdominant pairing channels such as  $s$ -wave or  $d_{xy}$ -wave channels are still possible.<sup>6-8</sup> The mixed state of  $s + d$  superconductors was first discussed by Ruckenstein *et al.*<sup>9</sup> and that of  $d + is$  superconductors by Kotliar<sup>10</sup>. In Ref.[10], it is pointed out that the resonating-valence-bond mechanism can lead to  $s$ -wave and  $d$ -wave-like Cooper pairings, and a mixture of  $s$  and  $d$  waves with a well-defined relative phase close to  $\theta = \pi/2$  is energetically favored. Importantly, the superconducting state is time-reversal-symmetry (T hereafter) breaking and the energy gap is nodeless unless  $\theta = 0$  or  $\pi$ . Moreover, surfaces and interfaces, grain boundaries, and other pair-breaking defects have all been shown to enhance the T-breaking states.<sup>11,12</sup>

The vortex structure and vortex dynamics of  $d$ -wave superconductor have been studied numerically in detail by several methods<sup>13-17</sup>. Previous simulations for the  $d + is$ -wave superconductors showed that the vortex structure of  $d + is$ -wave superconductor is different from that of the  $d$ -wave superconductor<sup>18</sup>: The spatial profile of the moduli of  $s$ - and  $d$ -wave components in the  $d + is$ -wave state has a two-fold symmetry, in contrast to the four-fold symmetry of the magnetic-field-induced  $s$ -wave component of  $d$ -wave superconductor. However, it turns out that such a  $d + is$  state can only be stabilized at extremely low temperatures. With increasing temperature, the amplitude of  $s$ -wave component decreases and its symmetry changes from two-fold to four-fold. Here we would like to extend our study to the vortex dynamics of  $d + is$  superconductors. For conventional superconductors the free-flux-flow (FFF) resistance is linear in the magnetic field induction  $B$  (with  $B \ll B_{c2}$ ). The situation is not clear yet for high- $T_c$  and other unconventional superconductors. Because of the multiple components of the order parameter, this topic is highly nontrivial.

We also study the vortex motion in the presence of a twin-boundary and the intrinsic Hall effect of  $d + is$ -wave superconductors.

We start with a model of an isotropic two-dimensional Fermi liquid with attractive interactions in both  $s$ - and  $d$ -channels. Obviously, when only one of the two interactions is attractive, the ground state is a pure state with the appropriate pairing symmetry. When both channels are attractive, the competition will lead to either a pure or a mixed pairing function. The GL theory for a superconductor with two attractive channels has been presented by Ren, Xu, and Ting<sup>19</sup> based on Gor'kov equations. Assuming pure dissipative dynamics, the GL equations can be expressed as follows:

$$0 = \left[ \eta_s \partial t - \alpha_s + \frac{4}{3}(|S|^2 + |D|^2) + \Pi^2 \right] S + \frac{2}{3} D^2 S^* + \frac{1}{2} (\Pi_x^2 - \Pi_y^2) D \quad (1)$$

$$0 = \left[ \eta_d \partial t - \alpha_d + \frac{8}{3}|S|^2 + |D|^2 + \Pi^2 \right] D + \frac{4}{3} S^2 D^* + (\Pi_x^2 - \Pi_y^2) S \quad (2)$$

$$0 = \frac{\partial \mathbf{A}}{\partial t} + \kappa^2 (\nabla \times \nabla \times \mathbf{A} - \nabla \times \mathbf{H}_e) + \left\{ S^* \Pi S + \frac{1}{2} D^* \Pi D + \frac{1}{2} [S^* (\Pi_x - \Pi_y) D + D^* (\Pi_x - \Pi_y) S] + \text{H.c.} \right\} \quad (3)$$

In these equations, the two order parameters,  $S$  and  $D$ , are normalized by  $\Delta_0 = \sqrt{4/3\alpha \ln(T_d/T)}$  with  $\alpha \approx 7\zeta(3)/8(\pi T_c)^2$ , the space by the coherence length  $\xi$ , and the vector potential  $\mathbf{A}$  by  $\Phi_0/2\pi\xi$  with  $\Phi_0 = h/2e$  being the flux quantum, respectively. In Eq.(1),  $\alpha_s$  may be expressed as a function of temperature  $T$ :<sup>19,20</sup>

$$\alpha_s = \ln(T_s/T)/\ln(T_d/T) \quad (4)$$

where  $T_s$  and  $T_d$  may be viewed as the apparent superconducting transition temperatures for the  $s$ -wave and the  $d$ -wave respectively, with  $T_s \propto e^{-\frac{1}{N(0)V_s}}$  and

$T_d \propto e^{-\frac{2}{N(0)V_d}}$ .  $\alpha_d = 1$  unless specified otherwise. Here  $N(0)$  is the density of states at the Fermi surface,  $V_s$  and  $V_d$  are the effective attractive interaction strengths in the  $s$ - and  $d$ -wave channels, respectively.  $\Pi = i\nabla + \mathbf{A}$ ,  $\Pi_k = \hat{x}_k \Pi_k$ .  $\kappa$  is the GL parameter. The time  $t$  is normalized by  $\tau = \sigma_n \xi^2$  with  $\sigma_n$  the normal-state conductivity of the superconductor.  $\eta_{s,d} = \tau_{s,d}/\tau$ , with  $\tau_{s,d}$  being the relaxation time of the  $s$ - and  $d$ - wave order parameters, respectively. For gapless conventional superconductors, the relaxation time of the order parameter near  $T_c$  is  $\tau_s = \pi\hbar/8k(T_c - T) \propto \xi^2$ .<sup>21</sup> For unconventional superconductors, it is plausible to assume the general scaling law  $\tau_{s,d} \sim \xi^z$  with  $z$  as the dynamical exponent, which should hold at least near the critical temperature. In this case, it is clear that  $\eta_{s,d} \sim \xi^{z-2}$  would depend on temperature if  $z \neq 2$ . However, in the absence of a microscopic theory on the relaxation times, we shall content ourselves to treat them as phenomenological parameters, the effect of which on the vortex dynamics is examined in this paper.

The scale for the magnetic field is set by the upper critical field  $H_{c2}$ . Because of its nontrivial nature in the present system, we would like to discuss it before moving to the dynamical properties of the vortices. Following the same method described by Sigrist *et al.*<sup>22</sup>, and using the relation  $[\Pi_x, \Pi_y] = iB$ , we introduce a pair of operators  $a = \frac{1}{\sqrt{2B}}(\Pi_x + i\Pi_y)$ ,  $a^\dagger = \frac{1}{\sqrt{2B}}(\Pi_x - i\Pi_y)$ , and have the commutative relation  $[a, a^\dagger] = 1$ . Substituting  $a, a^\dagger$  into the linearized Eq.(1) and Eq.(2) in the static case, we obtain:

$$\begin{aligned} (-2\alpha_s + 2B(1 + 2\hat{n}))S + B(aa + a^\dagger a^\dagger)D &= 0, \\ (-1 + B(1 + 2\hat{n})D + B(aa + a^\dagger a^\dagger)S &= 0, \end{aligned} \quad (5)$$

where  $\hat{n} = a^\dagger a$ . Therefore, the order parameter can be expanded in this occupation representation as  $\Psi = \sum_{m=0}^{\infty} \begin{pmatrix} s_m | m \rangle_s \\ d_m | m \rangle_d \end{pmatrix}$ , where  $\hat{n} | m \rangle = m | m \rangle$ . Eq.(5) can not be solved exactly, so we treat it variationally by assuming  $\Psi = \begin{pmatrix} s_0 | 0 \rangle_s \\ d_0 | 0 \rangle_d \end{pmatrix} + \begin{pmatrix} s_2 | 2 \rangle_s \\ d_2 | 2 \rangle_d \end{pmatrix} + \begin{pmatrix} s_4 | 4 \rangle_s \\ d_4 | 4 \rangle_d \end{pmatrix}$ .  $H_{c2}$  is determined by the condition that the ground state energy of the eigenvalue problem Eq.(5) is zero. It turns out that the variational ground state is  $\Psi = \begin{pmatrix} 0 \\ d_0 | 0 \rangle_d \end{pmatrix} + \begin{pmatrix} s_2 | 2 \rangle_s \\ 0 \end{pmatrix} + \begin{pmatrix} 0 \\ d_4 | 4 \rangle_d \end{pmatrix}$ , and the corresponding  $H_{c2}$  is given by the root of the equation

$$60B^3 - 86B^2 + 9\alpha_s B^2 + (10 - 10\alpha_s)B + \alpha_s = 0. \quad (6)$$

The temperature dependence of  $H_{c2}$  calculated in this way is shown as the solid line in Fig.(1). Here we use Eq.(4) for the temperature dependence of  $\alpha_s$ , and assume  $T_d = 100K$  and  $T_s = 90K$ . In order to check the reliability of the variational treatment, we also simulate the upper critical field of such a  $d+is$  superconductor numerically by solving Eq.(1)  $\sim$  Eq.(3) with the finite element method. In practice, we fix the magnetic field induction

$B$  by specifying one or two vortices in a square unit cell with periodic boundary conditions. The side length is varied so as to change the magnetic induction  $B$ . The technical details of the simulation have been given elsewhere.<sup>17</sup> The external magnetic field  $H$  can be derived from the Virial relation.<sup>23</sup> With  $H$  the Gibbs free energy density can be constructed, as shown in Fig.2. We can read off  $H_{c1}$  from the intersection of Meissner state line and the mixed-state line, and  $H_{c2}$  from the intersection of the mixed-state line and the normal-state line. The simulation result for the upper critical field is shown as black squares in Fig.1. The variational result (solid line) appears to be in excellent agreement with the simulation result, indicating that expanding the trial wave function up to the occupation state of  $|4\rangle$  is already rather reliable.<sup>24</sup> Note that  $H_{c2}$  is larger than that of the pure  $d$ -wave superconductor, which is always  $B_0 = \Phi_0/2\pi\xi^2$  in our case. From Fig.2, it is obvious that the magnetic field-induced transitions at  $H = H_{c1}$  and  $H = H_{c2}$  are both of the usual second order transition, which should be compared to the unusual first order transitions found numerically in some  $p$ -wave superconductors.<sup>25</sup>




FIG. 1. The upper critical field  $H_{c2}/B_0$  as a function of temperature  $T$  with  $B_0$  as the upper critical field of pure  $d$ -wave. The solid line is the approximation result determined from Eq.(6). The scatter point is the numerical result. Here  $T_s$  is set to 90K,  $T_d$  is set to 100K.




FIG. 2. Free vortex flow resistivity as a function of the applied field for  $\eta_s = 1, 10$ , and  $0.01$ . Here  $\alpha_s = 0.97, 0.85, 0.67$ , and  $-1$  in (a), (b), (c), and (d) respectively.

We now discuss the vortex flow driven by a transport current  $\mathbf{J}$  in the mixed state (i.e., with  $B < H_{c2}$ ). This is realized by requiring  $\nabla \times \mathbf{H}_e = \mathbf{J}$  in Eq.(3). Here we have chosen a gauge in which the electrostatic potential does not appear, so that the local electric field is simply  $\mathbf{E} = -\partial_t \mathbf{A}$ . To investigate the relaxation effects of the order parameter on the FFF resistivity, we chose three values of the relaxation coefficient of the order parameter  $S$  and  $D$  as : (1)  $\eta_s = 2\eta_d = 1$ , (2)  $\eta_s = 2\eta_d = 10$  ( $\gg 1$ ), (3)  $\eta_s = 2\eta_d = 0.01$  ( $\ll 1$ ). The field dependence of the FFF resistivity is shown in Fig.3. Noticeably it evolves from a convex to a concave with increasing  $\eta_s$ , albeit slight difference exists at the four temperatures shown in the four panels. This is the correct trend by general reasoning: The motion of vortices is equivalent to the phase slipping of the order parameter,<sup>26</sup> so that a small relaxation time means a quick rate of phase slipping, and thus a large resistance. Thus, with increasing magnetic field the vortex flow resistivity approaches the normal state resistivity more quickly. It follows from Fig.3 that the effect of the relaxation time is more prominent at lower temperatures (or larger  $\alpha_s$ ).




FIG. 3. Free vortex flow resistivity as a function of the applied field for  $\eta_s = 1, 10$ , and  $0.01$ . Here  $\alpha_s = 0.97, 0.85, 0.67$ , and  $-1$  in (a), (b), (c), and (d) respectively.

Next, we investigate the vortex motion of the  $d+is$  superconductor in the presence of twin-boundaries and then look into the pinning effect. A periodic array of twin-boundaries (with a transverse spacing of  $L = 10.8\xi$ ) are assumed and described by  $\alpha_i = \alpha_{i,0} - u_i \sum_k \delta(y - y_0 - kL)$ , where the subscript  $i$  stands for  $s$  or  $d$ . Here,  $u_i$  describes the variation of  $\alpha_{s,d}$  across the twin boundary along the line  $y = y_0$  due to the local mis-orientation or chemical contamination. Along the twin-boundary, we apply a transport current  $\mathbf{J} = J\hat{x}$ . The vortex motion will be pinned by the twin-boundary up to a depinning current  $J = J_c$ , which we shall determine. In the following simulation we fix  $\eta_s = 2\eta_d = 1$ . Figure 4 gives the current dependence of the flux-flow resistivity, which turns out to be highly nonlinear. In the present simulation, we may expect a simple result of the overdamped vortex motion in a periodic pinning potential:  $\rho/\rho_n = a\sqrt{1 - (J_c/J)^2}$  at  $J \geq J_c$  (the solid lines in Fig.4),<sup>17</sup> where  $a$  is the asymptotic reduced resistivity and  $J_c$  can be thus determined. We see that a higher depinning current arises from higher values of  $u_s$  (or  $u_d$ ). This is because of the increasing suppression of the amplitudes of  $s$ - wave and  $d$ - wave components at the boundary. In fact, with a suppression of the order parameter at the twin, the vortices lose less condensation energy, and thus have a lower energy than they would do in the bulk. For a  $d$ - wave superconductor,  $u_s$  is irrelevant because  $\alpha_s < 0$ , only  $u_d$  takes effect, so it is reasonable that a  $d$ - wave superconductor has a lower depinning current than a  $d+is$  superconductor does with the same twin boundary.




FIG. 4. The current dependence of the flux-flow resistivity in the presence of a twin-boundary. The solid lines represent the fitting at low  $J$  (see the text).

Finally, we turn our attention to the so called intrinsic Hall effect, which occurs for anisotropic vortex structures even without considering normal Hall conductivity  $\sigma_H^n$ . Alvarez *et al.* have found that in  $d$ - wave superconductors

the intrinsic Hall effect depends on the orientation angle,  $\varphi$ , of the driving current roughly as  $\sim \sin(4\varphi)$ , and increases nonlinearly with  $\mathbf{J}$ .<sup>27</sup> It is believed that this effect is due to the four-lobe structure of the  $d$ - wave vortices. So here we would like to explore the effect of the two-fold symmetry of  $s$ - and  $d$ - components on the intrinsic Hall effect. As usual, the intrinsic Hall effect is measured by  $\tan\theta_H = E_{AV,\perp}/E_{AV,\parallel}$ , where  $\mathbf{E}_{AV}$  and  $E_{AV,\perp}$  are the components of  $\mathbf{E}_{AV}$  perpendicular and parallel to the applied current, respectively. Figure 5 presents  $\tan\theta_H$  versus  $\varphi$  for (a) a  $d$ - wave superconductor with  $\alpha_s = -1.0$  and  $\alpha_d = 1.0$ ; (b) a  $d+is$ - wave superconductor with  $\alpha_s = 0.85$  and  $\alpha_d = 1.0$ . Here  $B = 0.034B_{c2}$ , and  $|\mathbf{J}| = 0.08$  at which  $\bar{\rho}/\rho_n \approx 0.6$  in both cases (a) and (b). It can be seen that for the  $d$ - wave superconductor (Fig. 5(a)),  $\tan\theta_H$  has two peaks (at  $\varphi_p = 15^\circ$  and  $\varphi_p = 75^\circ$ ), and is identically zero at  $\varphi = 0^\circ, 45^\circ$ , and  $90^\circ$ . For the  $d+is$  superconductor,  $\tan\theta_H$  is still zero at  $\varphi = 0^\circ, 45^\circ$  and  $90^\circ$ , but there are new sign reversals at approximately  $\varphi = 22.5^\circ$  and  $67.5^\circ$ . Clearly, the vanishing of  $\tan\theta_H$  at  $\varphi = 0^\circ, 45^\circ$  and  $90^\circ$  can be attributed to the fact that the vortex (and thus the supercurrent around it) can adjust its symmetry axis to the the direction of the driving force from the the applied current. At other directions of the driving force, the vortex can only partially adjust its symmetry axis. The new sign reversal for the  $d+is$  superconductors is more subtle. In this case, the vortex profile is two-fold symmetric. Therefore, there are two non-equivalent configurations for the vortex to have its (reflection) symmetry axis along the  $x$ ,  $y$ , or the diagonal directions. We suspect that the abnormal sign reversal results from a switching between these two meta-stable configurations as the direction of the driving force changes.




FIG. 5.  $\tan\theta_H$  as function of the current orientation angle  $\varphi$  at  $|\mathbf{J}| = 0.08$  and  $B = 0.034B_{c2}$ . (a)  $\alpha_s = -1.0$  and  $\alpha_d = 1.0$ ; (b)  $\alpha_s = 0.85$ ,  $\alpha_d = 1.0$ . The lines are guides for the eye.

In summary, the dynamics of the vortices in both  $d+is$ -wave and  $d$ -wave superconductors is studied. The upper critical field of the  $d+is$ -wave superconductors is studied

analytically and numerically. From simulation results, the curvature of the FFF resistivity as a function of the magnetic field strongly depends on the relaxation rate of the order parameter. The flux flow in the presence of a twin boundary is also addressed. Finally, the intrinsic Hall effect of  $d$ - and  $d+is$ - wave superconductors are studied numerically. We find the orientation dependence of the intrinsic Hall effect in these two types of superconductors are rather different.

This work was supported by the RGC grant of Hong Kong under No. HKU 7116/98P and a CRCG grant at the University of Hong Kong. Q.H.W. was supported by the National Natural Science Foundation of China and in part by the Ke-Li Fellowship financed by Sanzhu Co. Ltd. in Shandong of China.

- 
- <sup>1</sup> D. A. Wollman, D. J. Van Harlingen, J. Giapintzakis, and D. M. Ginsberg, Phys. Rev. Lett. **74**, 797 (1995).
  - <sup>2</sup> I. Iguchi and Z. Wen, Phys. Rev. B **49**, 12388 (1994).
  - <sup>3</sup> J. H. Miller, Jr. *et al.*, Phys. Rev. Lett. **74**, 2347 (1995).
  - <sup>4</sup> C. C. Tsuei *et al.*, Phys. Rev. Lett. **73**, 593(1994).
  - <sup>5</sup> A. Mathai, Y. Gim, R. Black, A. Amar and F. C. Wellstood, Phys. Rev. Lett. **74**, 4523(1995).
  - <sup>6</sup> A. G. Sun, D. A. Gajewski, M. B. Maple and R. C. Dynes, Phys. Rev. Lett. **72**, 2267 (1994).
  - <sup>7</sup> J. Ma, C. Quitmann, R. J. Kelley, H. Berger, G. Margaritondo, and M. Onellion, Science **267**, 862 (1995).
  - <sup>8</sup> H. Ding, J. C. Campuzano, and G. Jennings, Phys. Rev. Lett. **74**, 2784(1995).
  - <sup>9</sup> A. E. Ruckenstein, P. J. Hirschfeld, and J. Apel, Phys. Rev. B **36**, 857 (1987).
  - <sup>10</sup> G. Kotliar, Phys. Rev. B **37**, 3664 (1988).
  - <sup>11</sup> J. R. Kirtley, P. Chaudhari, M. B. Ketchen, N. Khare, S. Y. Lin, and T. Shaw, Phys. Rev. B **51**, 12057 (1995).
  - <sup>12</sup> M. Sigrist, D. B. Bailey, and R. B. Laughlin, Phys. Rev. Lett. **74**, 3249 (1995); D. B. Bailey, M. Sigrist, and R. B. Laughlin, Phys. Rev. B **55**, 15239 (1997); K. Kuboki and M. Sigrist, J. Phys. Soc. Jpn. **65**, 361 (1996).
  - <sup>13</sup> P. I. Soininen, C. Kallin, and A. J. Berlinsky, Phys. Rev. B **50**, 13883 (1994).
  - <sup>14</sup> J. H. Xu, Y. Ren, and C. S. Ting, Phys. Rev. B **53**, R2991 (1996).
  - <sup>15</sup> A. J. Berlinsky, A. L. Fetter, M. Franz, C. Kallin, and P. I. Soininen, Phys. Rev. Lett. **75**, 2200 (1995); M. Franz, C. Kallin, P. I. Soininen, A. J. Berlinsky, and A. L. Fetter, Phys. Rev. B **53**, 5795 (1996).
  - <sup>16</sup> R. Heeb, A. van Otterlo, M. Sigrist, and G. Blatter, Phys. Rev. B **54**, 9385 (1996).
  - <sup>17</sup> Q. Wang and Z. D. Wang, Phys. Rev. B **54**, R15645 (1996); Z. D. Wang and Q. H. Wang, Phys. Rev. B **55**, 11756 (1997).
  - <sup>18</sup> Q. Li, Z. D. Wang, and Q. H. Wang, Phys. Rev. B **59**, 613(1999).
  - <sup>19</sup> Y. Ren, J. H. Xu, and C. S. Ting, Phys. Rev. B **53**, 2249

- (1996).
- <sup>20</sup> The physical properties as a function of temperature discussed later are only qualitative, as the present  $T$ -dependence of  $\alpha_s$  is not quantitatively rigorous in the whole temperature range.
  - <sup>21</sup> L. P. Gor'kov, and G. M. Eliashberg, Zh. Eksperim. Teor. Fiz. **54**, 612(1968) [Soviet Phys. JETP **27**, 328 (1968)].
  - <sup>22</sup> M. Sigrist and K. Ueda, Rev. Mod. Phys. **63**, 239 (1991)
  - <sup>23</sup> M. M. Doria, J. E. Gubernatis, and D. Rainer, Phys. Rev. B **39**, 9573 (1989); Z. D. Wang and C. -R. Hu, Phys. Rev. B **44**, 11918 (1991); Z. D. Wang, E. M. Y. Kwok, and P.C. W. Fung, Z. Phys. B **97**, 409 (1995).
  - <sup>24</sup> W. Kim, J. X. Zhu, and C. S. Ting, Phys. Rev. B **58**, R607 (1998).
  - <sup>25</sup> Z. D. Wang and Q. H. Wang, Phys. Rev. B **57**, R724,(1998); Q. H. Wang and Z. D. Wang, Phys. Rev. B **57**, 10307,(1998).
  - <sup>26</sup> M. Tinkham, *Introduction to Superconductivity* (McGraw-Hill, New York, 1975).
  - <sup>27</sup> J. J. Vicente Alvarze, D. Dominguez, and C. A. Balseiro, Phys. Rev. Lett. **79**, 1373(1997).